



# UltraSOLV® Wipers, Swabs and Sponges

## Chemical Resistance Datasheet



*cleaning critical surfaces*

Resistance to ASTM D543 (30-day saturation)

Chemical	Temperature	% wt Change <sup>1</sup>	Observation	Chemical	Temperature	% wt Change <sup>1</sup>	Observation
Acetone	23°C	- 1.5	unaffected	Methanol	23°C	- 1.7	unaffected
	50°C	- 3.9	softened		50°C	- 5.1	unaffected
Sodium Hydroxide	23°C	- 8.0	discolored, brittle	MEK	23°C	- 0.8	discolored
	50°C	- 18.1	discolored, brittle		50°C	- 6.7	softened
Ammonia hy	23°C	- 0.1	unaffected	Mineral Oil	23°C	+19.0	unaffected
	50°C	- 0.9	softened		50°C	+17.8	unaffected
Benzene	23°C	- 0.1	unaffected	Oils/Fats	23°C	+9.3	unaffected
	50°C	- 0.9	softened		50°C	+8.8	unaffected
Ethyl Alcohol	23°C	- 1.1	unaffected	Phos Acid 10%	23°C	- 0.1	unaffected
	50°C	- 6.6	softened		50°C	- 3.8	softened
Ethyl Ether	23°C	- 0.3	unaffected	Sulfuric Acid .02N	23°C	- 0.2	unaffected
	50°C	- 3.8	softened		50°C	- 4.6	softened
Ethyl Acetate	23°C	- 1.0	unaffected	Detergent	23°C	+2.7	unaffected
	50°C	- 4.2	softened		50°C	+3.3	softened
Freon	23°C	- 0.2	unaffected	Toulene	23°C	- 4.0	unaffected
	50°C	- 2.6	discolored, softened		50°C	- 6.9	softened
HCl 1%	23°C	- 2.3	discolored, brittle	Tricloroethane	23°C	- 0.6	unaffected
	50°C	- 12.4	severe attack		50°C	- 7.5	softened
IPA 2-propanol	23°C	- 0.9	unaffected	Xylene	23°C	- 0.1	discolored
	50°C	- 5.7	unaffected		50°C	- 5.9	softened

<sup>1</sup> There is always a value for percent change in volume, similar to the value for percent change in weight.

Call Practical Tools now to speak with one of our knowledgeable, expert sales engineers. No matter what your application and cleaning needs are, Practical Tools is dedicated to providing the perfect solution for your requirements quickly, easily, and at the right price!